

---

**Product Name:** Rockhard Green Tinted Epoxy Stoving Enamel

---

**Product Number:** 690-450-005

---

**Product Description:** Rockhard green tinted epoxy stoving enamel is made to the same formula as the Rockhard clear but has a dye added to aid spraying. It is one of the best protective coatings for metals, particularly Aluminium and Magnesium. Used for example as an erosion resistant coating on blades in the Rolls Royce Pegasus engine.

690-450-005 coatings have been widely used in the aircraft industry where maximum protection is needed on Aluminium, Steel, Titanium and Magnesium. One particular application is on the stator blades and other engine components on aircraft serving on aircraft carriers (e.g. the Harrier) where maximum protection against marine and other harsh environments is needed.

---

**Approvals/Specifications:**

- DTD 5562
- MSRR 9228, OMat 7 / 146
- Previously 444 / 226
- Nato Stock No (NSN): 8010-99-608-3363

---

**Components:** Single Pack Product. May be thinned for application using 665-550-025

---

**Performance:** Tested to DTD 5562 including 6 months intermittent salt spray (DEF 1053 method 36).

Resistant to humidity, trichloroethylene baths and re-chromating

Meets the requirements of multiple specifications to include:

- Salt Spray: 1,000 hours to ASTM-B117 (non-scribed)
  - High Temperature: 1,000 hours @ 220°C
  - Low Temperature Resistance: 24 hours @ -50°C
  - Aerospace Fuel Resistance: 48 hours @ 40±2°C
-

## Application:

<b>Surface Preparation:</b>	Substrates must be clean, dry and grease free. Bare metal adhesion is improved through abrasion or grit blasting. Normally applied to clean metal or pre-treated substrate. May be used as an adhesion promoting coating on some composite substrates.
<b>Paint Preparation:</b>	Single pack range of products – may be applied at supply viscosity. Thinning with up to 20% IP-Reducer may be required upon application.
<b>Application Method:</b>	Apply by spray; conventional or HVLP. For full details, refer to Indestructible Application Guide IPAS-21. Request RPS661/34 for Rolls Royce Parts.
<b>Drying Curing:</b>	<p><b>Air Dry:</b> 15 minutes</p> <p>Part Bake between coatings: 150±10°C for 30-60 minutes</p> <p>Full Cure (standard): 190±5°C for 60-90 minutes</p> <p>Care must be taken to comply with end user requirements where customer approval to an alternative baking schedule has been agreed.</p>

## Technical Properties:

<b>Supply Viscosity:</b>	Clear, 19-24 seconds ISO5 @ 23±2°C
<b>Flash Point:</b>	24°C
<b>VOC Content:</b>	675 g/litre
<b>Colour:</b>	Green Transparent
<b>Pack Size:</b>	1 and 5 litre
<b>Density:</b>	0.96 kg/litre
<b>Gloss:</b>	Gloss
<b>Thinner:</b>	665-550-025
<b>Solvent/Clean Up:</b>	40006 Gun Cleaner
<b>Catalyst:</b>	N/A
<b>Theoretical Coverage:</b>	11.7 sq m/litre @ 20 micron

---

**Storage:**

Highly flammable liquid: store and use in accordance with the flammable liquid regulations

**Shelf Life:** 12 months temperate; 6 months tropical

**Before use, refer to Product Safety Data Sheet**

---

**Disclaimer:**

The information printed in this publication is based upon the research and experience of Indestructible Paint Ltd. No representation of warranty is made, however, concerning the accuracy or completeness of the information presented in this publication. Indestructible Paint Ltd make no warranty or representation of any kind, express or implied. Including without information limitation any warranty or merchantability or fitness for any particular purpose, and no warranty or representation shall be implied by law or otherwise. Any products sold by Indestructible Paint Ltd are not warranted as suitable for any particular purpose to the buyer. The suitability of any products for any purpose in particular to the buyer is for the buyer to determine. Indestructible Paint Ltd assumes no responsibility for the selection of products suitable to the particular purpose of any particular buyer. Indestructible Paint Ltd shall in no event be liable for any special, incidental or consequential damages.

---

**Safety Data Sheets:**

For Safety Data Sheets please contact our Sales Department:

Tel: +44(0)121 702 2485

Email: [sales@indestructible.co.uk](mailto:sales@indestructible.co.uk)