
Product Name: Graphite Filled Skydrol Resistant Dry Film Lubricant

Product Number: IP9136-R1

Product Description: Spray applied, stoving cured, silicon resin modified dry film lubricant for use where high operating temperatures preclude the use of conventional oils and greases.

Suitable for application to steel, aluminium, magnesium and titanium alloys.

Used on, for example spherical bearing surfaces to protect against frottage corrosion and on bolts for torque and gives an exceptionally good rubbing wear resistance.

When used on bolts, it increases torque end loads. It is also used on turbine blade roots and fir trees where it reduces the likelihood of the disc splitting.

Approvals/Specifications:

- Turbomeca Spec LB 541
- MSRR9276, CPW 27, AMS 3132 (Graphite filled), RR Code 110565, OMAT 4/44C
- CoMat #10 – 002, NSN 9150-99-500-0559, Kawasaki – JMSRR 9276, Honeywell Phoenix Arizona PCS 5022, GEC Marconi 1608/0038/001, SNECMA spec P1064, JAEC JCR – 024, MTU – MTS 1173

Alternative to the following:

- PL239 (3862X9010) AFS473, which was originally PL239; Superseded PL 94 in about 1984
-

Performance:

Resistant to dry heat up to 400°C (750°F) in oxidizing atmospheres and 500°C (930°F) where oxygen is excluded, ester lubricants, Skydrol and corrosion.

Tri-n-Butyl-Phosphate: 3 hours @ 70°C

Dry Heat: 1000 hours at 400°C

Technical Data Sheet



Components:

Single Part Product. May be thinned for application using IP985-Reducer or IP9151 Thinner

Application:

Surface Preparation:

Ensure that surfaces are clean and free from dirt

Paint Preparation:

Stir well before use. All separated material must be re-incorporated into the bulk product. No time limits are specified for the mixing operation. The operator must be satisfied that the product including any thinning solvent is thoroughly mixed before use. Where mechanical mixing is employed care must be taken to not heat the product to above the maximum storage temperature. Mixing in open containers should be limited to <10 minute periods to ensure that solvent evaporation does not compromise the product. Shaking or rolling in closed containers is an acceptable mixing method for small volume products supplied ready for use.

Application Method:

Spray a light coat and allow to dry for 10 minutes, stove for 2 hours at 190°C (375°F). Where spraying is not possible small areas may be coated by brush.

Refer to RPS 661 / 10 for additional details.

Drying Curing:

Air Dry:

10 minutes then stove for 2 hours at 190°C (375°F)

Technical Properties:

Supply Viscosity:	Ready for use
Flash Point:	27°C
VOC Content:	N / A
Colour:	Grey
Pack Size:	1 & 5 Litres
Density:	1.05 kg / litre
Gloss:	N / A
Thinner:	IP9151
Solvent/Clean Up:	40006 Gun Cleaner

Technical Data Sheet



Catalyst:	Ready for use
Theoretical Coverage:	10.5 sq m/litre @ 25 micron

Storage:	Highly flammable liquid: store and use in accordance with the flammable liquid regulations
-----------------	--

Shelf Life: 12 months temperate; 6 months tropical

Before use, refer to Product Safety Data Sheet

Disclaimer:

The information printed in this publication is based upon the research and experience of Indestructible Paint Ltd. No representation of warranty is made, however, concerning the accuracy or completeness of the information presented in this publication. Indestructible Paint Ltd make no warranty or representation of any kind, express or implied. Including without information limitation any warranty or merchantability or fitness for any particular purpose, and no warranty or representation shall be implied by law or otherwise. Any products sold by Indestructible Paint Ltd are not warranted as suitable for any particular purpose to the buyer. The suitability of any products for any purpose in particular to the buyer is for the buyer to determine. Indestructible Paint Ltd assumes no responsibility for the selection of products suitable to the particular purpose of any particular buyer. Indestructible Paint Ltd shall in no event be liable for any special, incidental or consequential damages.

Safety Data Sheets:

For Safety Data Sheets please contact our Sales Department:

Tel: +44(0)121 702 2485

Email: sales@indestructible.co.uk
