
Product Name:

Green Ipseal H/T Inorganic. Seal. MSRR9140

Product Number:

IP9184-GREEN

Product Description:

Ipseal is an inorganic protective coating used as a barrier on Ipcote IP9183-R1, IP9253, PL219, Ipthin IP9356.

All of the Ipcote coatings are conductive, sacrificial coatings and inherently porous. Ipseal seals this porosity without detracting from their sacrificial properties. It also creates an electrically non-conductive barrier coat. The use of Ipseal on top of these products results in a smoother, harder coating which provides a barrier against carbon deposits etc extending the useful life of the base coat and a smoother finish which enhances airflow characteristics and therefore engine efficiency.

IP9184 is for use at temperatures up to 800°C (1400°F). This material also has capabilities as a coating in its own right, being water based with no VOC's, this coating has high temperature resistance up to 800°C on such metals as nickel. It has shown a 70% reduction in Alpha Case corrosion on titanium at 650°C at 3-5 microns.

For repair touch up's refer to PL270 Khaki.

Approvals/Specifications:

- MSRR 9140 (Previously MSRR9355)
 - IP9184-KH-R1 Green; Rolls Royce Code: 139265
 - Omat 7/168B – Green
 - NSN: 8030-99-434-2295
 - Turbomeca LB714
 - Alternative to Sermaseal 570
-

Performance:

- Tested to specification MSRR 9140 (under test to CPW 404)
 - Smooth eggshell finish
 - Typical film thickness 4-6 microns per coat (0.2 thou)
 - Operating temperature -40°C to 800°C (1420°F)
 - Less than 0.6% hexavalent chrome
-

Components:

Singe Pack Product. May be thinned with water for spray application. Where low humidity is present within a spray facility the addition of 5-10% by volume of water may be required.

Application:

Surface Preparation:

Ensure that surfaces are clean and dirt free.

Paint Preparation:

Stir well before use. All separated materials must be re-incorporated into the bulk product. No time limits are specified for the mixing operation. The operator must be satisfied that the product including any thinning solvent is thoroughly mixed before use. Where mechanical mixing is employed care must be taken to not heat the product to above the maximum storage temperature. Mixing in open containers should be limited to <10 minute periods to ensure that solvent evaporation does not compromise the product. Shaking or rolling in closed containers is an acceptable mixing method for small volume products supplied ready for use.

Application Method:

Spray applied coating. Refer to application sheet IPAS666

Drying Curing:

- **Air Dry:** 10 minutes
 - **Heat Cure:** Pre-bake for 30 minutes @ 80-100°C, 30-60 minutes @ 350°C
-

Technical Properties:

Supply Viscosity:	37-43 ISO3 Cup @ 23°C
Solids:	45-51
Flash Point:	N/A
VOC Content:	0g / l
Colour:	Green
Pack Size:	1 and 5 Litre
Density:	1.3kg / litre
Gloss:	N/A
Thinner:	Water
Solvent/Clean Up:	Water
Theoretical Coverage:	29.8 sq m / l @ 10 micron

Technical Data Sheet



Storage:

Shelf Life: 12 months temperate; 6 months tropical

Before use, refer to Product Safety Data Sheet

Disclaimer:

The information printed in this publication is based upon the research and experience of Indestructible Paint Ltd. No representation of warranty is made, however, concerning the accuracy or completeness of the information presented in this publication. Indestructible Paint Ltd make no warranty or representation of any kind, express or implied. Including without information limitation any warranty or merchantability or fitness for any particular purpose, and no warranty or representation shall be implied by law or otherwise. Any products sold by Indestructible Paint Ltd are not warranted as suitable for any particular purpose to the buyer. The suitability of any products for any purpose in particular to the buyer is for the buyer to determine. Indestructible Paint Ltd assumes no responsibility for the selection of products suitable to the particular purpose of any particular buyer. Indestructible Paint Ltd shall in no event be liable for any special, incidental or consequential damages.

Safety Data Sheets:

For Safety Data Sheets please contact our Sales Department:

Tel: +44(0)121 702 2485

Email: sales@indestructible.co.uk