

---

**Product Name:**

Mica Impregnated Insulating Coating

---

**Product Number:**

PL95-R1

---

**Product Description:**

PL95-R1 is an insulating coating for application to aero engine components. It will give excellent resistance to heat, corrosion, lubricants, coolants and fuels.

The cured coating can be machined to produce accurate dimensions on working surfaces.

This product has been evaluated by Rolls Royce as having conductivity of  $2.2 \times 10$  watts/meter/°C in 1972.

The R1 version has been re-formulated to comply with new environmental requirements, this modification has made it easier to apply a thicker coating.

---

**Approvals/Specifications:**

- MSRR 9054
  - Rolls Royce Code: 139007
  - 4862 C 8095
  - E3745
  - OMat 773
- 

**Performance:**

PL95-R1 has been tested to the following: tests show a minimum specification and are exceeded by actual performance:

- |  |           |
|--|-----------|
| - Dry heat resistance at 500°C (930°F):            | 100 hours |
| - Ester Lubrication resistance at 150°C (300°F):   | 100 hours |
| - Skydrol resistance at room temperature:          | 100 hours |
| - Skydrol resistance at 70°C (160°F) at room temp: | 3 hours   |
| - Salt water fog resistance:                       | 100 hours |
- 

**Components:**

Single Pack Product.

---

## Application:

**Surface Preparation:** Ensure that all surfaces are clean and free from dirt, grease and oil.

**Paint Preparation:** Shake/ stir well before use. This product is highly pigmented and will settle on storage.

**Application Method:** Apply with conventional spray using the following technique:

- Apply one coat and allow to stand for 3 minutes
- Apply a second coat and either:
  - o Air dry for 30 minutes
  - o Stove at 65-75°C (150-175°F) for 20 minutes
- Apply further wet on wet coatings with subsequent air drying or stoving until the required thickness is obtained – usually 3 applications

**Drying Curing:**

- If air drying between coats has been used; 30 minutes at 145-155°C (295-310°F), followed by 2 hours at 185-195°C (365-385°F)
- If stoving has been used between coats; 2 hours at 185-195°C (365-385°F), after 30 minutes flash off.

## Technical Properties:

<b>Supply Viscosity:</b>	2500 to 2700 CPS
<b>Flash Point:</b>	27°C
<b>VOC Content:</b>	-
<b>Colour:</b>	Slate Grey
<b>Pack Size:</b>	1 & 5 Litres
<b>Density:</b>	1.28kg/l ± 2%
<b>Gloss:</b>	Semi-Matt
<b>Thinner:</b>	IP9151
<b>Solvent/Clean Up:</b>	IP9151 or 40006 Gunwash
<b>Catalyst:</b>	N/A
<b>Theoretical Coverage:</b>	-

---

**Storage:**

Highly flammable liquid: store and use in accordance with the flammable liquid regulations

**Shelf Life:** 12 months temperate; 6 months tropical

**Before use, refer to Product Safety Data Sheet**

---

**Disclaimer:**

The information printed in this publication is based upon the research and experience of Indestructible Paint Ltd. No representation of warranty is made, however, concerning the accuracy or completeness of the information presented in this publication. Indestructible Paint Ltd make no warranty or representation of any kind, express or implied. Including without information limitation any warranty or merchantability or fitness for any particular purpose, and no warranty or representation shall be implied by law or otherwise. Any products sold by Indestructible Paint Ltd are not warranted as suitable for any particular purpose to the buyer. The suitability of any products for any purpose in particular to the buyer is for the buyer to determine. Indestructible Paint Ltd assumes no responsibility for the selection of products suitable to the particular purpose of any particular buyer. Indestructible Paint Ltd shall in no event be liable for any special, incidental or consequential damages.

---

**Safety Data Sheets:**

For Safety Data Sheets please contact our Sales Department:

Tel: +44(0)121 702 2485

Email: [sales@indestructible.co.uk](mailto:sales@indestructible.co.uk)